














# PERFORMANCE CHARACTERISTICS

## ANTISKID/ EMBOSSED

CHARACTERISTICS	TEST METHOD	RESULT
THICKNESS	 EN 428	2.00 MM AND 3.0 MM
SHEET	 EN 430	3.6 KG AND 5.25 KG/SQ.MTR.
DIMENSIONAL STABILITY	 EN 434	<0.50%
REACTION OF FIRE	 BS 476 PART 6 & PART 7	PASSED
FLEXIBILITY	 EN 435	< 20 MM PASSED
SLIP RESISTANCE	 DIN 51130	R11
ABRASION RESISTENCE	 EN 660-2 EN 649	PASSED
RESIDUAL INDENTATION	 EN 433	<0.10 MM
CASTOR CHAIR	 EN 425	WITHOUT DAMAGE OF SURFACE ACCORDING TO EN 649 TABLE
LIGHT FASTNESS	 ISO 105-B02	BLUE WOOL STANDARD 6
STAIN AND CHEMICAL RESISTANCE	 EN 423	NO VISIBLE CHANGE
FUNGI AND FACTERIA RESISTANCE		DOES NOT FAVOUR GROWTH
PERFORMANCE CLASSIFICATION	 EN 685	33, 34